

**Amendments to the Specification:**

EC  
7-11-08

Please replace the paragraph ~~39~~<sup>19</sup> beginning on page ~~2~~<sup>33</sup> and continuing onto page 3 with the following paragraph:

FIGS. 2 and 3 illustrate the provision of, respectively, two and three inner layers "A"/"B" pairs of coatings. The repetition of "A"/"B" layers is what finally gives a multi-layer structure. The greater the number of "A"/"B" pairs, the better the reliability of a window. That is, the probability of the occurrence of pinholes is lower, but the manufacturing cost is higher. The total surface density of the coating preferably does not exceed about  $0.3 \text{ mg/cm}^2$ . Practically, the number of "A"/"B" pairs is usually one to five.